

SFIBRAL GAMA is a high density non combustible fiber cement wall panel with fire micro laminate as top layer.

200 decors in mono colors, wood and other decors available.

Technical data

Version: January 2023.

Properties	Standard	Unit	GAMA 4	GAMA 7	GAMA 9
Nominal thickness		mm	4 mm	7 mm	9 mm
Standard sizes (trimmed)		mm	2510 x 1250 3050 x 1250	2510 x 1250 3050 x 1250	2510 x 1250 3050 x 1250
Density		kg / m ³	1900 ± 50	1900 ± 50	1900 ± 50
Tolerance thickness		mm	± 0,2	± 0,2	± 0,2
Tolerance lenght		mm	± 5	± 5	± 5
Tolerance width		mm	± 4	± 4	± 4
Fire behavior	DIN EN 13501-1		A2,s1,d0	A2,s1,d0	A2,s1,d0
Elasticity modulus		N / mm ²	≥ 12.000	≥14.700	≥15.600
Tensile bending strenght		Mpa	≥ 45	≥ 51	≥ 58
Fmax		N	111	480	565
Expansion		%	0,58	0,6	0,62
Brinell hardness	EN ISO 650-1	HBW 6,25/3,18	99,5	99,5	99,5
Falling ball test	EN 438-T2	mm	2	2	2
Scratch resistance	EN 438-2:2016	N	3	3	3
Abrasion resistance	EN 438-2:2016	Rotation	≥ 150	≥ 150	≥ 150
Resistance against dry heat	EN 438-2:2005	Grade	4	4	4
Resistance against watter vapour	EN 438-2:2005	Grade	4	4	4
Adhesion	DIN EN ISO 4624	N/mm ²	1,29	1,29	1,29
Resistance against impact of health sector equipment	DIN 13411:1999-02	---	OK according standard	OK according standard	OK according standard

Resistance to chemicals

Bose Sterillium	ISO 19712	Level1	Grade 5	Grade 5	Grade 5
Terralin Protect	ISO 19712	Level1	Grade 5	Grade 5	Grade 5
Sensiva hand disinfection	ISO 19712	Level1	Grade 5	Grade 5	Grade 5
Chlor concentrate	ISO 19712	Level1	Grade 5	Grade 5	Grade 5
Chlor 8g / 100g water	ISO 19712	Level1	Grade 5	Grade 5	Grade 5
Chlor 10mg / 1 Ltr. Water	ISO 19712	Level1	Grade 5	Grade 5	Grade 5

This data sheet has been prepared to the best of our knowledge and corresponds to our state of knowledge at the above-mentioned date of publication. All data and information are based on tests carried out by ourselves or commissioned by our suppliers. All data are of a purely informative nature and do not represent any assurance of specific product properties. The suitability of the product described must be checked on your own responsibility or in consultation with our application engineering department. We also reserve the right to make technical changes that may affect the data described. The up-to-dateness of the available data is to be enquired about if necessary.